

GARWARE SUNCONTROL® WINDOW FILM				NON REFLECTIVE FILMS								
				PRODUCT DESCRIPTION: As the name states, these non-reflective films offer extremely faster installations, to Assure immediate customer satisfaction.								
Type of Films	Thickness	Visible Light Transmittance	Visible Light Reflectance	Solar Energy Transmittance	Solar Energy Reflectance	Solar Energy Absorbance	Ultra Violet Transmittance	Glare Reduction	Shading Coefficient	Emissivity	U Factor (BTU /HR./SQ.FT.)	Total Solar Energy Rejection
NR GREY 5	1 Mil	4%	6%	41%	6%	53%	<1%	96%	0.64	0.85	1.12	44%
NR GREY 15	1 Mil	16%	6%	44%	6%	50%	<1%	82%	0.67	0.86	1.14	42%
NR GREY 35	1 Mil	35%	6%	54%	7%	39%	<1%	62%	0.76	0.86	1.14	35%
NR GREY 50	1 Mil	50%	6%	58%	7%	35%	<1%	45%	0.78	0.86	1.14	32%
NR GREY 60	1 Mil	60%	7%	62%	7%	31%	<1%	34%	0.81	0.86	1.15	29%
NR CHARCOAL 5	1 Mil	5%	5%	39%	6%	55%	<1%	95%	0.64	0.85	1.12	45%
NR CHARCOAL 20	1 Mil	21%	5%	45%	6%	49%	<1%	77%	0.68	0.86	1.15	42%
NR CHARCOAL 35	1 Mil	35%	6%	53%	7%	40%	<1%	62%	0.75	0.86	1.12	36%
NR CHARCOAL 50	1 Mil	51%	6%	60%	7%	33%	<1%	44%	0.80	0.86	1.14	31%
NR BRONZE 15	1 Mil	17%	6%	48%	7%	45%	<1%	81%	0.71	0.86	1.13	39%
NR BRONZE 35	1 Mil	30%	6%	48%	7%	45%	<1%	67%	0.71	0.86	1.14	39%
NR GREEN 20	1 Mil	21%	6%	43%	6%	51%	<1%	77%	0.66	0.86	1.14	43%
NR GREEN 35	1 Mil	36%	7%	50%	7%	43%	<1%	60%	0.72	0.86	1.14	37%
NR GREEN 50	1 Mil	53%	7%	60%	7%	33%	<1%	42%	0.80	0.86	1.14	31%
NR BLACK 5	1 Mil	5%	6%	44%	7%	49%	<1%	95%	0.66	0.85	1.12	42%
NR BLACK 20	1 Mil	20%	6%	47%	7%	46%	<1%	78%	0.69	0.86	1.14	40%
NR BLACK 35	1 Mil	35%	6%	52%	7%	41%	<1%	62%	0.73	0.86	1.12	37%
NR BLACK 50	1 Mil	50%	6%	61%	7%	32%	<1%	45%	0.80	0.86	1.13	30%
NR BLACK 70	1 Mil	70%	7%	70%	9%	21%	<1%	23%	0.87	0.86	1.13	24%



Disclaimer: The Performance data reported on this page was tested at DSET Lab & MATRIX Lab, USA ASHRAE, and ASTM & AIMCOL standards. All Value as applied to 1/8 inch (3mm) glass. Tests are representative of actual product sample & may vary from batch to batch.